

Mirafi[®] TM13C

Mirafi[®] TM13C is a 3-dimensional, lofty synthetic, erosion control mat, which provides bare soil retention, vegetation nurturing and turf reinforcement. Mirafi[®] TM13C is inert to biological degradation and resists naturally encountered chemicals, alkalis, and acids.

TenCate Geosynthetics Americas Laboratories are accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program ([GAI-LAP](#)).

PERFORMANCE PROPERTIES ¹	TEST METHOD	UNIT	VALUE
Velocity (fully vegetated)	Large Scale	ft/sec (m/sec)	>25 (7.6)
Shear Stress (fully vegetated)	Large Scale	lbs/ft ² (Pa)	16.9 (809)
Manning's Coefficient	Calculated	"n"	0.033

MECHANICAL PROPERTIES	TEST METHOD	UNIT	MINIMUM AVERAGE ROLL VALUE	
			MD	CD
Tensile Strength @ Ultimate	ASTM D6818	lbs/ft (kN/m)	3096 (45.2)	3096 (45.2)
MINIMUM TEST VALUE				
UV Resistance (at 3000 hours)	ASTM D4355	% strength retained	98	
UV Resistance (at 6000 hours)	ASTM D4355	% strength retained	90	
UV Resistance (at 10000 hours) ³	ASTM D4355	% strength retained	83	
TYPICAL ROLL VALUE				
Thickness	ASTM D6525	mils (mm)	475 (10.2)	
Resiliency	ASTM D6524	%	70	
Resiliency ²	ASTM D6524	mils (mm)	330 (8.4)	
MAXIMUM ROLL VALUE				
			MD	CD
Tensile Elongation	ASTM D6818	%	50	50
Light Penetration	ASTM D6567	%	40	

PHYSICAL PROPERTIES	TEST METHOD	UNIT	TYPICAL ROLL SIZE
Mass Per Unit Area	ASTM D6566	oz/yd ² (g/m ²)	9.0 (288)
Roll Dimensions (width x length)			12' x 75' (3.66m x 22.9m)
Estimated Roll Weight			
Label Roll Color			Green or Tan ³

¹ Based upon full-scale independent testing performed at TRI Environmental.

² Typical Resiliency Thickness reported in mils, *T_f* per Section 9.5, ASTM D6524.

³ UV Resistance (@10000 hours) not available for Tan PATENT # 8,252,705

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Mirafi[®] is a registered trademark of Nicolon Corporation. Copyright © 2021 Nicolon Corporation. All Rights Reserved

FGS000735
ETQR13