

Mirafi[®] MTK



Mirafi[®] MTK is a self-adhering waterproofing membrane designed especially for pavement reflective crack control and as a moisture barrier to prevent water permeation or penetration through pavement surfaces and the subsequent damage that moisture causes in the roadway sub-base.

TenCate Geosynthetics Americas Laboratories are accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

Mechanical Properties ¹	Test Method	Unit	Minimum Average Roll Value
Thickness	ASTM D1777 ²	mils (mm)	65 (1.7)
Grab Tensile Strength	ASTM D4632	lbs (N)	160 (712)
Grab Tensile Elongation	ASTM D4632	%	60
Puncture Strength	ASTM E154	lbs (N)	200 (890)
Permeance	ASTM E96, Method B	perms	0.05 (max)
Strip Tensile	ASTM D882	lbs/in (kN/m)	50 (8.8)
Strip Elongation	ASTM D882	%	50
Melting Point	ASTM D276	F° (C°)	325 (163)
Pliability	ASTM D146 ¼" Mandrel 180° @ -25°F	No cracks in fabric or rubberized asphalt	

¹ Testing performed on composite

² ½" Presser Foot

Physical Properties	Unit	Typical Value			
Roll Dimensions (width)	in (m)	12 (0.3)	18 (0.5)	24 (0.6)	36 (0.9)
Roll Dimensions (length)	ft (m)	200 (61)	200 (61)	100 (30)	50 (15.2)
Roll Per Box	each	1	1	1	1

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

Mirafi[®] is a registered trademark of Nicolon Corporation.

Copyright © 2015 Nicolon Corporation. All Rights Reserved.

365 South Holland Drive
Pendergrass, GA 30567

Tel 706 693 2226
Tel 888 795 0808

Fax 706 693 4400
www.tencate.com

FGS000009
ETQR15

