

Mirafi[®] MPM30 (PGM-30)



Mirafi[®] MPM30 (PGM-30) is constructed of high strength glass filaments bonded to a polyester fabric. Mirafi[®] MPM (PGM-30) was especially developed for the rehabilitation of asphalt roads.

TenCate Geosynthetics Americas Laboratories are accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value
Tensile Strength @ 0°	ASTM D5035 (2C-E)	lbs	200
Tensile Strength @ 90°			200
Tensile Elongation	ASTM D5035	%	< 5
			Minimum Test Value
Melting Point	ASTM D276	F° (C°)	450° (232°)
Asphalt Retention	ASTM D6140	gal/yd ²	0.10
Mass/Unit Area	ASTM D5261	oz/yd ²	4.0

Physical Properties	Unit	Roll Characteristics	
Roll Dimensions (width x length)	ft	10 x 450	12.5 x 360
Roll Area	yd ²	500	500
Estimated Roll Weight	lbs	172	172

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

Mirafi[®] is a registered trademark of Nicolon Corporation.

Copyright © 2015 Nicolon Corporation. All Rights Reserved.

365 South Holland Drive
Pendergrass, GA 30567

Tel 706 693 2226
Tel 888 795 0808

Fax 706 693 4400
www.tencate.com

FGS000789
ETQR7

