



Mirafi® G200N Drainage Composite

G200N Drainage Composite is produced from a perforated, high compressive strength polymer core with an AASHTO M288 Class 3 nonwoven with elongation $\geq 50\%$ filter geotextile bonded to both sides.

TenCate Geosynthetics Americas Laboratories are accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

CORE MECHANICAL PROPERTIES	TEST METHOD	UNIT	TYPICAL ROLL VALUE	
Thickness	ASTM D1777	in (mm)	0.4 (10.2)	
Compressive Strength	ASTM D1621	psf (kPa)	18,000 (862)	
Maximum Flow rate ¹	ASTM D4716	gal/min/ft (l/min/m)	21 (260)	

GEOTEXTILE MECHANICAL PROPERTIES AASHTO M288 CLASS 3 NONWOVEN	TEST METHOD	UNIT	MINIMUM AVERAGE ROLL VALUE	
			MD	CD
Grab Tensile Strength	ASTM D4632	Unit	120 (534)	120 (534)
CBR Puncture Strength	ASTM D6241	Unit	310 (1380)	
Apparent Opening Size (AOS)	D4751	Unit	70 (0.212)	

			MINIMUM ROLL VALUE	
Permittivity	D4491	sec ⁻¹	1.7	
Flow Rate	D4491	gal/min/ft ² (l/min/m ²)	135 (5500)	

PHYSICAL PROPERTIES	UNIT	TYPICAL ROLL VALUE
Roll Dimensions (width x length)	ft (m)	4 x 50 (1.2 x 15.2)
Roll Area	ft ² (m ²)	200 (18.6)
Estimated Roll Weight	lb (kg)	50 (22)
Label Roll Color		WHITE

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Mirafi® is a registered trademark of Nicolon Corporation. Copyright © 2021 Nicolon Corporation. All Rights Reserved

FGS000539
ETQR11