


Mirafi® CR440



Mirafi® CR440 is composed of high-tenacity polypropylene yarns, which are woven into a network such that the yarns retain their relative position. Mirafi® CR440 is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value	
			MD	CD
Tensile Strength (at ultimate)	ASTM D4595	lbs/ft (kN/m)	7200 (105)	10620 (155)
Tensile Strength (at 5% strain)	ASTM D4595	lbs/ft (kN/m)	1500 (21.9)	5400 (78.8)
CBR Puncture	ASTM D6241	lbs (N)	2700 (12015)	
			Minimum Roll Value	
Flow Rate	ASTM D4491	gal/min/ft ² l/min/m ²	30 (1222)	
			Typical Roll Value	
Pore Size O ₉₅	ASTM D6767	microns	577	
Pore Size O ₅₀	ASTM D6767	microns	265	
			Maximum Opening Size	
Apparent Opening Size (AOS)	ASTM D4751	U.S. Sieve (mm)	30 (0.60)	
			Minimum Test Value	
Factory Seam Strength	ASTM D4884	lbs/ft (kN/m)	5652 (82.5)	
UV Resistance (at 500 hours)	ASTM D4355	% strength retained	85	

Physical Properties	Unit	Typical Value
Roll Dimensions (width x length)	ft (m)	15 x 300 (4.5 x 91)
Roll Area	yd ² (m ²)	500 (418)

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

Mirafi® is a registered trademark of Nicolon Corporation.

Copyright © 2016 Nicolon Corporation. All Rights Reserved.

