

## Miragrid® 22XT

Miragrid® 22XT geogrid is composed of high molecular weight, high tenacity polyester multifilament yarns woven in tension and finished with a PVC coating. Miragrid® 22XT geogrid is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

Miragrid 22XT geogrid is used as soil reinforcement in MSE structures such as segmental retaining walls, precast modular block walls, wire faced walls, geosynthetic wrapped faced walls and steepened slopes. Miragrid 22XT is also used in MSE stabilized platforms for voids bridging, embankments on soft soils, landfill veneer stability, reducing differential settlement and for foundation seismic stability.

TenCate Geosynthetics Americas is accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program ([GAI-LAP](#)).

| MECHANICAL PROPERTIES                         | TEST METHOD           | UNIT                                   | MINIMUM AVERAGE ROLL VALUE |
|---|-----------------------|--|----------------------------|
|   |                       |  | MD                         |
| Tensile Strength @ Ultimate                   | ASTM D6637 (Method B) | lbs/ft (kN/m)                          | 20559 (300.0)              |
| Tensile Strength @ 5% strain                  | ASTM D6637 (Method B) | lbs/ft (kN/m)                          | 6700 (97.8)                |
| Mass/Unit Area <sup>1</sup>                   | (ASTM D5261)          | oz/yd <sup>2</sup> (g/m <sup>2</sup> ) | 28.2 (956)                 |
|   |                       |  | <b>MINIMUM ROLL VALUE</b>  |
| Creep Rupture Strength <sup>2</sup>           | ASTM D5262/D6992      | lbs/ft (kN/m)                          | 14277 (208.3)              |
| Long Term Design Strength <sup>3</sup>        |                       | lbs/ft (kN/m)                          | 12361 (180.4)              |
| PHYSICAL PROPERTIES                           |                       | UNIT                                   | ROLL CHARACTERISTIC        |
| Roll Dimensions <sup>4</sup> (width x length) |                       | ft (m)                                 | 12 x 200 (3.6 x 61)        |
| Roll Area                                     |                       | yd <sup>2</sup> (m <sup>2</sup> )      | 267 (220)                  |
| Estimated Roll Weight                         |                       | lbs (kg)                               | 470 (213)                  |
| Label Roll Color                              |                       |  | WHITE                      |

<sup>1</sup> Typical Value

<sup>2</sup> 75-year design life based on NTPEP Report [REGEO-2016-01-069](#).

<sup>3</sup> Long Term Design Strength for sand, silt, clay.  $RF_{CR} = 1.44$ ;  $RF_{ID} = 1.05$ ;  $RF_D = 1.1$  (Installation damage reduction factor for other soils available upon request).

<sup>4</sup> Special order roll lengths are available upon request

Disclaimer: TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice. Mirafi™ is a registered trademark of Nicolon Corporation. Copyright © 2021 Nicolon Corporation. All Rights Reserved  
 FGS000105  
 ETQR19