

MIRAGRID 8XT

chemicals, alkalis, and acids.

MIRAGRID® 8XT uniaxial geogrid is composed of high molecular weight, high tenacity polyester multifilament yarns woven in tension

MIRAGRID 8XT geogrid is used as soil reinforcement in MSE structures such as segmental retaining walls, precast modular block walls, wire faced walls, geosynthetic wrapped faced walls and steepened slopes. MIRAGRID 8XT is also used in MSE stabilized platforms for voids bridging, embankments on soft soils, landfill veneer stability, reducing differential settlement and for foundation seismic stability. TenCate Geosynthetics Americas (A Solmax Company) is accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

and finished with a PVC coating. MIRAGRID 8XT geogrid is inert to biological degradation and resistant to naturally encountered

MIRAFI 8XT meets Build America, Buy America Act, Pub. L. No. 117-58, div. G §§ 70901-52.

MECHANICAL PROPERTIES	TEST METHOD	UNIT	MINIMUM AVERAGE ROLL VALUE MD
Tensile Strength @ Ultimate	ASTM D6637(Method B)	lbs/ft (kN/m)	7600 (110.9)
Tensile Strength @ 5% strain	ASTM D6637(Method B)	lbs/ft (kN/m)	2600 (37.9)
			MINIMUM ROLL VALUE
Creep Rupture Strength <sup>1</sup>	ASTM D5262/D6992	lbs/ft (kN/m)	5278 (77.0)
Long Term Design Strength <sup>2</sup>		lbs/ft (kN/m)	4570 (66.7)
PHYSICAL PROPERTIES		UNIT	ROLL SIZE
Roll Dimensions <sup>3</sup>			6 x 300 (1.8 x 91)
		ft (m)	12 x 200 (3.6 x 46)
(width x length)			12 x 1000 (3.6 x 305)
			200 (167)
Roll Area		yd² (m²)	267 (220)
			1333 (1114)
			140 (64)
Estimated Roll Weight		lbs (kg)	205 (93)
			975 (442)

<sup>&</sup>lt;sup>1</sup>75-year design life based on NTPEP Report <u>REGEO-2016-01-066</u>.







 $<sup>^2</sup>$  Value based on Long Term Design Strength for sand, silt, clay. RF<sub>CR</sub> = 1.44; RF<sub>ID</sub> = 1.05; RF<sub>D</sub> = 1.1 (Installation damage reduction factor for other soils available upon request)

<sup>&</sup>lt;sup>3</sup> Special order roll lengths are available upon request.